



FULL BODY



60x120 cm
60x60 cm
30x60 cm

ITALCRAFTS[®]
Tiles. To build the future.

FULL
BODY

ITALCRAFTS®
FULL BODY

DOLOMINE



FACES 01

FORMAT



FINISHES


POLISHED
MATT



DOLOMINE

FULL
BODY

DOLPHIN



FORMAT



FINISHES


POLISHED
MATT
ROCK

www.italcrafts.it



FULL
BODY

GRAPHITE



FACES 01

FORMAT



FINISHES

POLISHED
MATT
ROCK

www.italcrafts.it




GRAPHITE

FULL
BODY

ITALCRAFTS®
FULL BODY

CHARCOAL BLACK




FACES 01

FORMAT



FINISHES

POLISHED
MATT




CHARCOAL BLACK

FULL
BODY

ITALCRAFTS®
FULL BODY

SNOW WHITE




FACES 01

FORMAT



FINISHES

POLISHED
MATT




SNOW WHITE

FULL
BODY

ITALCRAFTS®
FULL BODY

STEEL GREY



FORMAT



FINISHES

POLISHED
MATT

FACES 01
















STEEL GREY

GLAZED PORCELAIN EN14411 B1A

TEST

TEST - ENSAYO - PRÜFUNG - TESTER

	EN value	OUR VALUE
 <p>LENGTH AND WIDTH MEASURE MISURA DI LUNGHEZZA E LARGHEZZA MEDIDA DE LARGO Y ANCHO LÄNGE UND BREITENMASSNAHME MESURE DE LA LONGUEUR ET DE LA LARGEUR</p>	±0.6% Max. ±2mm	±0.2%
 <p>THICKNESS MEASURE MISURA DI SPESORE MEDIDA DE ESPESOR DICKENMESSUNG MESURE D'ÉPAISSEUR</p>	±5% Max. ±0.5mm	±5.0%
 <p>MEASURE OF THE STRAIGHTNESS OF THE SIDES MISURA DELLA RETTILINEZZA DEI LATI MEDIDA DE LA RECTITUD DE LOS LADOS MESSUNG DER GERADE DER SEITEN MESURE DE LA DROITE DES CÔTES</p>	±0.5% Max. ±1,5mm	±0.3%
 <p>MEASURE OF SQUARENESS MISURA DI SQUAREZZA MEDIDA DE CUADRADURA MESSUNG DER QUADRATUR MESURE DE CARRÉ</p>	±0.5% Max. ±2mm	±0.3%
 <p>MEASURE OF SURFACE FLATNESS MISURA DELLA PLANARITÀ DELLA SUPERFICIE MEDIDA DE LISO SUPERFICIAL MESSUNG DER FLACHHEIT DER OBERFLÄCHE MESURE DE LA PLANÉITÉ DE LA SURFACE</p>	±0.5% Max. ±2mm	±0.3%
 <p>WATER ABSORPTION ASSORBIMENTO DELL'ACQUA ABSORCIÓN DE AGUA WASSERAUFNAHME ABSORPTION DE L'EAU</p>	Average : ≤0.5%	≤0.2%
 <p>BENDING STRENGTH RESISTENZA ALLA FLESSIONE RESISTENCIA A LA FLEXIÓN Biegefestigkeit RÉSISTANCE À LA FLEXION</p>	Minimum : ≥35 N/mm ²	≥40 N/mm ²
 <p>BREAKING STRENGTH RESISTENZA ALLA ROTTURA FUERZA QUE ROMPE BRUCHFESTIGKEIT RÉSISTANCE À LA RUPTURE</p>	Thickness: ≥7.5 ≥1300N	≥1500 N

	EN value	OUR VALUE
 <p>RESISTANCE TO ABRASION RESISTENZA ALL'ABRASIONE RESISTENCIA A LA ABRASIÓN Beständigkeit gegen Abrieb RÉSISTANCE À L'ABRASION</p>	DECLARED VALUE	PEI 4
 <p>THERMAL SHOCK RESISTANCE RESISTENZA AGLI SHOCK TERMICI RESISTENCIA AL CHOQUE TÉRMICO WÄRMESCHOCKBESTÄNDIGKEIT RÉSISTANCE AUX CHOCs THERMIQUES</p>	REQUIRED NECESSARIA NECESARIA ERFORDERLICH OBLIGATOIRE	COMPLIES WITH THE STANDARD CONFORME ALLO STANDARD CUMPLE CON LA NORMA ENTSPRICHT DEM STANDARD CONFORME À LA NORME
 <p>FROST RESISTANCE RESISTENZA AL GELO RESISTENCIA A LAS HELADAS FROSTBESTÄNDIGKEIT RÉSISTANCE AU GEL</p>	REQUIRED NECESSARIA NECESARIA ERFORDERLICH OBLIGATOIRE	COMPLIES WITH THE STANDARD CONFORME ALLO STANDARD CUMPLE CON LA NORMA ENTSPRICHT DEM STANDARD CONFORME À LA NORME
 <p>CHEMICAL RESISTANCE RESISTENZA CHIMICA RESISTENCIA QUÍMICA CHEMISCHE RESISTENZ RÉSISTANCE CHIMIQUE</p>	Class : MIN UB	COMPLIANT
 <p>RESISTANCE TO STAINING RESISTENZA ALLE MACCHIE RESISTENCIA A LAS MANCHAS WIDERSTAND RÉSISTANCE AUX TACHES</p>	Class : MIN 3	Class : 4

.ITALCRAFTS[®]
Tiles. To build the future.

Add: Via Sacco e Vanzetti N22
41042 Fiorano Modenese, Italy.

Mail: info@italcrafts.it
Ph: +390536838911

www.italcrafts.it